



CREME DE LA CREME

SOLID - SKU #AH-750100
ENGINEERED - SKU #AH-625100

WAGNER

SOLID - SKU #AH-750102
ENGINEERED - SKU #AH-625102

COBB

SOLID - SKU #AH-750103
ENGINEERED - SKU #AH-625103

SPECIES:	ASH	Janka Hardness (ASTM D 1037):	1,320
CUT:	Plain Sawn	Flame Spread Class Rating (ASTM E 84):	Class III (C)
GRADE:	Select/Better	Flame Spread Index (ASTM E 84):	100
FINISH:	Matte Polyurethane	Smoke Developed Index (ASTM E 84):	100

NWFA/NOFMA grading guidelines:

SELECT GRADE: A flooring product with coloration variations produced by differences of natural heartwood and sapwood, along with characters described. The face may contain: unlimited sound sapwood; slight imperfections in milling; a small tight knot every 3'; pin worm holes; burls and a reasonable amount of slightly open checks. Brown streaks should not extend the entire length of a piece. Two flag worm holes to every 8' are permitted. Slight imperfections in face work (torn grain) admitted. An intermittent, brown machine burn across the face not exceeding 1/4" width admitted.

STANDARD MILLWORK:

Tongue & Groove, Endmatched

STANDARD DIMENSIONS & EDGE DETAIL:

	Solid	Engineered
Thickness:	3/4"	5/8" (4 mm wear layer)
Width:	5"	5"
Random Lengths:	2'-10'	2'-10'
Edges:	Microbevel	Microbevel

Note: Additional widths and lengths available upon request.

INSTALLATION GUIDE:

	Solid	Engineered
Above-grade	YES	YES
On-grade	YES	YES
Below-grade	NO	YES
Over Radiant Heat	YES	YES

ACCEPTABLE SUB-FLOORS and INSTALLATION METHODS - see installation guidelines for additional details and recommended adhesive:

Plywood Sub-floor : Glue-down, Nail-down, Staple-down
 Concrete Sub-floor: Glue-down

SUSTAINABLE ATTRIBUTES:

CERTIFICATION

Available as FSC-Certified

POSSIBLE LEED CREDITS

MR 5 - Regional Materials
 MR 7 - Certified wood (as FSC)
 EQ 4.4 - Low-emitting materials: Composite Wood & Agrifiber Products (Engineered)

Photo Disclaimer: Project and product photos are meant to be a general guide to product appearance only. Due to our handcrafted process and wood being a product of nature, the color, grain pattern, character and profile will vary between individual boards on a project and will never be an exact match.

Janka Rating from similarly tested products - expected to be close to actual measurements of reSAWN TIMBER co.'s products.

Data from Forest Products Laboratory (FPL) General Technical Report (GTR) 190 - expected to be close to actual measurements of reSAWN TIMBER co.'s products.